

## Stainless Steel Welding Electrode E 316L



Element	C	Mn	Si	Cr	Ni	Mo
Percent	0.035	1.75	0.45	18.5	12.5	2.3

[Read More](#)

**SKU:** E316L

**Price:**

**Stock:** instock

**Categories:** [Welding Consumables](#),  
[Stainless Steel Electrodes](#), [Welding Electrodes](#)

### Product Description

E 316L electrode is primarily used for welding low carbon molybdenum-bearing austenitic alloys. The weld metal displays good crack resistance, excellent creep strength and resists scaling at elevated temperatures up to 850°C. The weld metal has excellent resistance to corrosion and pitting.

Element	C	Mn	Si	Cr	Ni	Mo
Percent	0.035	1.75	0.45	18.5	12.5	2.3