

## E NiCrMo 6 Nickel Alloy Welding Electrodes



Element	C	Mn	Fe	Nb	S	Si	W	Cr	Mo	Ni
Percent	0.05	3.5	7.0	1.0	0.02	0.60	1.20	13.0	7.0	Bal
Element	Cr	Cb+Ta	Mo	W						
Percent	13	1.5	6	1.5						

[Read More](#)

**SKU:** ENiCrMo - 6

**Price:**

**Stock:** instock

**Categories:** [Welding Consumables](#),  
[Welding Electrodes](#), [Nickel Alloy Welding Electrodes](#)

### Product Description

An all position basic coated electrode depositing a nickel chromium based alloy with additions of molybdenum, tungsten and niobium. The electrode is especially designed for welding of 9% nickel steels for cryogenic applications down to -196°C. Typical application is land based LNG tanks.

Element	C	Mn	Fe	Nb	S	Si	W	Cr	Mo	Ni
Percent	0.05	3.5	7.0	1.0	0.02	0.60	1.20	13.0	7.0	Bal
Element	Cr	Cb+Ta	Mo	W						
Percent	13	1.5	6	1.5						