



ER 70S-G Carbon steel TIG Solid Welding Wire

Element	C	Mn	Si	S	P
Percent	0.06-0.14	1.60-1.90	0.80-1.15	0.025 max	0.025 max

[Read More](#)

SKU: ER 70S-G

Price:

Stock: instock

Categories: [Welding Consumables](#), [Welding Filler Wires](#), [TIG/MIG Filler Wires](#), [Carbon Steel Welding Wires](#)

Product Description

ER 70S-G is a coated, manganese-silicon alloyed GTAW wire for welding of all general engineering and structural steels with minimum yield strength of max 400 Mpa. High level of silicon and manganese for use on slightly contaminated base materials. contains deoxidizers also provide better wetting , giving a flatter bead shape and the capability of faster travel speeds. CHEMICAL

COMPOSITION OF ALL WELD METAL (%)

Element	C	Mn	Si	S	P
Percent	0.06-0.14	1.60-1.90	0.80-1.15	0.025 max	0.025 max