

## Stainless Steel AISI 304L MIG TIG Filler Wire



Element	C	Mn	Si	Cr	Ni
Percent	0.03	2.0	0.75	18	8

[Read More](#)

**SKU:** AISI 304L

**Price:**

**Stock:** instock

**Categories:** [Welding Consumables](#), [Welding Filler Wires](#), [TIG/MIG Filler Wires](#), [Stainless Steel Welding Wires](#)

### Product Description

AISI 304L is the low carbon version of AISI 304 (0.08%C) which may be susceptible to intergranular corrosion in certain corrosive media after it is welded or otherwise heated at temperatures between 430 and 860°C. For welded applications avoid the unstabilised, higher carbon, versions. CHEMICAL COMPOSITION OF ALL WELD METAL (%)

Element	C	Mn	Si	Cr	Ni
Percent	0.03	2.0	0.75	18	8