



## ER CuSn-A Tin Bronze MIG TIG Welding Wires

Element	Cu	Al	P	Pb	Sn
Percent	bal	0.01	0.1	0.02	4-6

[Read More](#)

**SKU:** ER CuSn-A

**Price:**

**Stock:** instock

**Categories:** [Welding Consumables](#), [Welding Filler Wires](#), [TIG/MIG Filler Wires](#), [Copper Alloy Welding Wires](#)

### Product Description

ER CuSn-A Phosphor Bronze A Electrode is useful for welding copper tin bronzes (Cu-Sn 6-8 %) and some brasses (Cu-Zn). Also suitable for joining wrought copper-tin bronzes and brasses to cast iron and carbon steel. This is recommended for repairing wrought bronzes (Cu-Sn); for surfacing on brasses, steels and cast iron. Some of other applications are as under: • Useful for Joining base metals of similar composition. • Construction of equipment for the chemical industry and petrochemical industry. • Naval constructions and installations for sea water desalination, repair works. COMPOSITION OF ALL WELD METAL (%)

Element	Cu	Al	P	Pb	Sn
Percent	bal	0.01	0.1	0.02	4-6