


ER CuNi Copro Nickel TIG MIG Welding Wire



Element	Cu	Fe	Mn	Ni	Si
Percent	bal	0.4-0.7	0.5-1.5	29	0.25

[Read More](#)

SKU: ER CuNi

Price:

Stock: instock

Categories: [Welding Consumables](#), [Copper Alloy Welding Wires](#), [TIG/MIG Filler Wires](#), [Welding Filler Wires](#)

Product Description

ER CuNi Copper Nickel Electrode offers excellent resistance to the corrosive effects of salt water, is widely used for marine and desalination applications such as Shipbuilding, seawater evaporation plants, tubes, pump building, offshore etc. Also suitable for welding of nonferrous alloys, Dissimilar steel materials. COMPOSITION OF ALL WELD METAL (%)

Element	Cu	Fe	Mn	Ni	Si
Percent	bal	0.4-0.7	0.5-1.5	29	0.25